

SUSTAINABILITY ASSESSMENT OF HIGH-PERFORMANCE CONCRETE STRUCTURES: A REVIEW OF MATERIALS, METHODS, AND DESIGN APPROACHES

Dr. M. Adil Khan^{*1}, Dr. Muhammad Shoaib Ahsraf², Shariqa Fakhar³

^{*1}Resident Engineer, NESPAK

²Senior Program Manager, Mecaer America Inc. Rue William-Price Laval Quebec Canada

³Sardar bahadur khan women's university Quetta

^{*1}adee.uol@gmail.com, ²m.ashraf@mecaer.com, ³shariqa.fakhar@yahoo.com

DOI: <https://doi.org/10.5281/zenodo.23391709>

Keywords

High-performance concrete, sustainability assessment, life cycle assessment, supplementary cementitious materials, carbon footprint

Article History

Received: 08 July 2026

Accepted: 29 September 2026

Published: 15 October 2026

Copyright @Author

Corresponding Author: *

Dr. M. Adil Khan

Abstract

High-performance concrete (HPC) represents an advanced class of cementitious materials offering superior strength, durability, and workability compared to conventional concrete. This review examines the sustainability assessment of HPC structures through comprehensive evaluation of materials, testing methodologies, and design approaches. The integration of supplementary cementitious materials (SCMs) such as fly ash, silica fume, and ground granulated blast furnace slag significantly reduces environmental impact while maintaining structural performance. Advanced testing methods including electrical resistivity, rapid chloride penetration, and carbonation resistance evaluation provide critical durability indicators. Life cycle assessment (LCA) frameworks demonstrate that optimized HPC designs incorporating waste materials can reduce carbon footprint by up to 80% while extending service life and minimizing maintenance requirements. Performance-based design methodologies coupled with machine learning optimization enable the development of sustainable concrete mixes that balance strength, cost, and environmental sustainability. This review synthesizes recent developments in HPC sustainability, highlighting the convergence of material innovation, computational technologies, and resilience-based design frameworks toward establishing adaptive and environmentally responsible infrastructure systems. Future advancement requires standardized testing protocols, regulatory frameworks, and continued integration of renewable materials to enable widespread adoption of sustainable HPC in construction.

1. INTRODUCTION

1.1 Context and Significance of High-Performance Concrete

Concrete is the most widely used construction material globally, with worldwide production contributing approximately 5% of all human-related CO₂ emissions annually (Al-Omari et al., 2023). High-performance concrete (HPC) has emerged as a transformative material that addresses both the technical demands of modern infrastructure and the pressing need

for environmental sustainability. Unlike conventional concrete, HPC offers enhanced mechanical properties, superior durability, and improved workability, enabling engineers to design slender, lightweight structures with extended service lives (Kayali, Haque and Khatib, 2008; Ali, 2023). The development of HPC represents a paradigm shift in construction practices, facilitating the creation of innovative structures spanning diverse

sectors including bridges, high-rise buildings, pavements, and marine environments.

The sustainability imperative driving HPC development stems from multiple sources. First, the production of Portland cement—a primary constituent of concrete—is inherently energy-intensive and generates significant greenhouse gas emissions through both fuel combustion and the calcination process (Kara, Erdem and Lezcano, 2021). Second, conventional concrete structures deteriorate prematurely in aggressive environments, requiring frequent maintenance and repair, which intensifies resource consumption and environmental burdens over their lifecycle. Third, urbanization and infrastructure development demands continue to accelerate, necessitating construction materials that can meet performance requirements while minimizing ecological footprint (Garg and Roy, 2026).

1.2 Sustainability Challenges and Drivers

The construction industry's environmental impact extends beyond production phases. Over the lifecycle of buildings, operational energy consumption dominates carbon emissions in many cases, contributing approximately 73% of total emissions in some residential applications (Garg and Roy, 2026). However, material selection remains critical, as concrete production constitutes a significant embodied energy component. The integration of supplementary cementitious materials (SCMs) provides a viable pathway to reduce cement content without compromising structural integrity (Gedam *et al.*, 2019). Materials such as fly ash, ground granulated blast furnace slag (GGBFS), silica fume, and metakaolin represent industrial by-products that would otherwise require disposal, simultaneously addressing waste management challenges while enhancing concrete sustainability (Kayali, Haque and Khatib, 2008).

1.3 Life Cycle Perspective and Performance-Based Design

Contemporary approaches to HPC sustainability emphasize lifecycle assessment (LCA) methodologies that quantify environmental impacts across all stages—from raw material extraction through disposal and potential recycling (Al-Omari *et al.*, 2023).

Performance-based design frameworks increasingly incorporate resilience considerations alongside durability, enabling structures to maintain functionality under evolving environmental conditions (Aznaw, 2025). The convergence of digital technologies, including Building Information Modelling (BIM), artificial intelligence, and advanced computational tools, provides engineers with unprecedented capabilities to optimize material selection, structural design, and construction practices for maximum sustainability benefit.

1.4 Objectives and Scope

This literature review synthesizes recent research on the sustainability assessment of HPC structures, examining three interconnected dimensions: (1) material composition strategies emphasizing supplementary cementitious materials and waste-derived additives, (2) testing methodologies for evaluating durability and environmental performance, and (3) design approaches integrating sustainability considerations into structural engineering practice. The review emphasizes the transition from prescriptive to performance-based design standards and highlights how advanced technologies including machine learning and lifecycle assessment enable more nuanced optimization of concrete systems for environmental sustainability.

2. METHODOLOGY

2.1 Research Framework and Literature Selection

This comprehensive literature review employs a systematic approach to synthesize research on HPC sustainability assessment. The research methodology integrates multiple databases including Scopus, Web of Science, and Google Scholar to ensure breadth and relevance of sources. The selection criteria prioritized peer-reviewed publications from the past decade addressing sustainability assessment of HPC materials, encompassing experimental studies, numerical modeling, lifecycle assessment case studies, and review papers. Keywords encompassed high-performance concrete, ultra-high performance concrete, supplementary cementitious materials, life cycle assessment,

carbon footprint, durability assessment, and

sustainable design methodologies.

2.2 Classification of Research Areas:

The selected literature was categorized into three primary research domains reflecting the paper's thematic organization. The first domain encompasses material composition and mix design optimization, including studies on SCMs integration, waste material utilization, and pozzolanic reaction mechanisms (Habibi, Ramezani pour and Mahdikhani, 2021; Hamada and Abed, 2024). The second domain addresses testing and assessment methodologies,

encompassing electrical resistivity measurements, chloride migration testing, freeze-thaw resistance evaluation, and carbonation assessment procedures (Saladi *et al.*, 2023). The third domain focuses on design frameworks, including lifecycle cost analysis, service life prediction models, performance-based design approaches, and integration of machine learning algorithms for optimization (Summa *et al.*, 2023; Gopu, 2025).

Table 1: Research Domains and Assessment Parameters

Research Domain	Primary Focus	Key Assessment Parameters
Material Composition	SCM integration and waste utilization	Compressive strength, workability, cost
Testing Methodologies	Durability and environmental performance	Resistivity, chloride penetration, carbonation depth
Design Frameworks	Optimization and lifecycle assessment	Service life, LCC, CO ₂ emissions, environmental impact

2.3 Sustainability Assessment Metrics

The review evaluates sustainability through multiple complementary metrics. Environmental impact assessment utilizes Global Warming Potential (GWP) expressed in kg CO₂-eq, embodied energy quantified in MJ/kg, and resource depletion indicators (Habibi, Ramezani pour and Mahdikhani, 2021). Economic sustainability is assessed through lifecycle cost analysis and initial

material cost considerations. Functional sustainability emphasizes service life prediction and durability performance, recognizing that extended structural life significantly reduces environmental impact per functional unit. The review adopts the functional unit approach recommended by LCA standards, moving beyond mass-based metrics to performance-based assessments that account for structural capacity and service life duration.

2.4 Testing and Evaluation Methods Analysis:

A comprehensive analysis of durability testing methodologies reveals significant variability in international standards for concrete assessment (Bernal *et al.*, 2024). The review evaluates conventional testing methods including ASTM C666 (freeze-thaw cycles), ASTM C1585 (water absorption), NT BUILD 492 (rapid chloride migration), and electrical resistivity measurements (AASHTO TP 119-22) (Saladi *et al.*, 2023). The assessment methodology examines the applicability of these established procedures to HPC and UHPC materials, which possess dense microstructures and fiber reinforcement that may not respond to conventional testing in expected ways. Non-

destructive testing methods including ultrasonic pulse velocity, dynamic modulus measurements, and gas permeability testing are evaluated as supplementary assessment tools.

2.5 Life Cycle Assessment Framework

The review integrates LCA methodology following ISO 14040 standards, examining system boundaries that typically include raw material acquisition, production phase, transportation, construction, use phase, and end-of-life stages (Summa *et al.*, 2023). A durability assessment-based design (DAD) workflow is highlighted, which combines structural design algorithms with durability performance prediction across intended service

life scenarios. This approach enables comparison between conventional reinforced concrete solutions and advanced HPC alternatives on equivalent functional bases, revealing that environmental benefit assessment requires consideration of maintenance frequency, service life extension, and potential for material reuse.

2.6 Machine Learning and Optimization Integration

Recent methodological advances employ artificial intelligence and machine learning models to predict HPC properties and optimize mix designs for sustainability objectives (Gopu,

2025; Parhi and Patro, 2025). The review examines various algorithms including Random Forest, Artificial Neural Networks, Support Vector Regression, and Gradient Boosting methods, which achieve prediction accuracy above $R^2 = 0.89$ for compressive strength and other key properties. Multi-objective optimization algorithms enable simultaneous maximization of structural performance while minimizing material cost and environmental impact. The integration of SHAP (SHapley Additive exPlanations) analysis provides interpretability to model predictions, bridging the gap between black-box machine learning and engineering decision-making.

Table 2: Testing Methodologies and UHPC Applicability

Testing Method	UHPC Applicability	Key Limitations
Electrical Resistivity	Excellent	Requires standardization
Freeze-Thaw Cycles	Limited	Low differentiation among UHPC mixes
Water Absorption	Limited	Dense matrix limits water ingress
Rapid Chloride Migration	Good	Complex interaction with fiber content
Carbonation Resistance	Good	Significant regional testing variability

2.7 Database and Comparative Analysis

The systematic review synthesized findings from over 40 peer-reviewed publications encompassing experimental studies on concrete mix designs, durability testing, LCA case studies, and computational optimization research. Comparative analysis examined environmental impact variations arising from different supplementary material choices, revealing that concrete mixes with 25-30% fly ash replacement achieve optimal balance between early-strength development and long-term sustainability benefit. Service life assessment across 50-year horizons demonstrates that environmental impact reduction of 60-80% is achievable through optimized mix design considering both material composition and maintenance requirements.

3. RESULTS

3.1 Material Performance and Environmental Impact

Supplementary cementitious materials integration represents the primary strategy for reducing HPC environmental footprint. Research demonstrates that replacing Portland cement with fly ash, GGBFS, or silica fume achieves measurable reductions in carbon emissions. A water tank constructed from UHPC incorporating waste-derived materials exhibited environmental impact reductions of up to 76% for human toxicity and freshwater aquatic ecotoxicity compared to ordinary reinforced concrete solutions, with overall embodied energy reduction of approximately 41-45% (Summa *et al.*, 2023). These reductions occur primarily through two mechanisms: (1) displacement of Portland cement with lower-impact materials, and (2) optimization of structural design enabled by HPC's superior mechanical properties, permitting reduced

material volume while maintaining load-bearing capacity.

The most effective SCM combinations incorporate multiple materials in ternary blending systems. Concrete mixes containing 20% fly ash and 50% slag achieved superior durability, with chloride permeability Emission reductions

approximately 43% relative to conventional mixes (Tushar *et al.*, 2025). Metakaolin-based concretes show particularly strong performance in marine environments, exhibiting resistance to chloride attack through both physical and pozzolanic mechanisms while reducing chemical CO₂ emissions (Pillay *et al.*, 2020).

The incorporation of waste-derived materials demonstrates substantial environmental benefits. Glass powder substitution for cement and silica fume in UHPC reduced embodied CO₂ emissions by 28.7% (175 kg per ton) while maintaining superior mechanical properties and improved durability characteristics (Wilson

reductions of 68% compared to conventional concrete (Mousa, Abed and Shukur, 2025). Similarly, geopolymer concrete incorporating binary combinations of GGBS and fly ash demonstrated compressive strength of 41 MPa at 28 days while eliminating Portland cement entirely, with carbon of

et al., 2019). Recycled concrete powder coating with graphene oxide enhances hydration while reducing environmental impact, achieving CO₂ emission reductions of 28.7% and primary energy requirement reductions of 28.5% per ton of material (Wang *et al.*, 2025). Crushed dune sand integration in HPC formulations achieves 11.4% improvement in 28-day compressive strength compared to reference concrete while generating substantially lower environmental impact (0.0013 kg CO₂/kg material), demonstrating the viability of locally-sourced materials in sustainable HPC development (Rennani *et al.*, 2025).

Table 3: Environmental and Durability Performance of Supplementary Materials

Supplementary Material	Cement Replacement Level	GWP Reduction	Chloride Resistance Improvement
Fly Ash	20-30%	15-25%	35-45%
Slag	40-50%	20-30%	50-60%
Silica Fume	5-10%	8-12%	40-50%
Metakaolin	10-15%	12-18%	45-55%
Binary Blends	25-35%	30-40%	60-70%

3.2 Durability Assessment and Service Life Prediction

Advanced testing methodologies reveal durability performance variations among HPC formulations. Electrical resistivity testing provides the most reliable durability indicator for UHPC, with strong correlation ($R^2 > 0.85$) between electrical resistivity and chloride migration coefficient (Saladi *et al.*, 2023). UHPC specimens exhibited electrical resistivity values substantially exceeding conventional concrete, indicating superior resistance to ionic transport and environmental degradation. Water-cured, non-air-entrained HPC demonstrated satisfactory performance through 1500 freeze-thaw cycles, while steam-cured variants showed reduced durability,

highlighting the significance of curing methodology in determining long-term performance (Soeda, Yamato and Emoto, 1999). Service life prediction models incorporating probabilistic frameworks demonstrated that 25% fly ash replacement substantially delays time to first corrosion-induced crack and reduces repair frequency. Probabilistic analysis of coastal structures with 50-year design service life revealed repair cost reductions of 40% through optimized mix composition (Hasnat and Manzur, 2025). Combined with larger concrete cover specifications, high-volume SCM replacement achieved CO₂ emission reductions of approximately 60% compared to conventional design approaches. These analyses emphasize that sustainability assessment must

incorporate functional service life, as extended durability significantly improves environmental benefit per unit performance.

Freeze-thaw and scaling resistance studies on HPC containing GGBFS and silica fume demonstrated excellent performance, with negligible scaling losses after 100 cycles and durability factors exceeding 90%, indicating minimal degradation (Soeda, Yamato and Emoto, 1999). Long-term alkali-silica reaction investigation in high-altitude regions revealed that internal damage in HPC remained minimal with appropriate admixtures, though surface damage progression required monitoring (Guo *et al.*, 2024). Carbonation resistance assessment across different standardized testing procedures revealed significant variability in results, emphasizing the critical importance of standardized testing protocols for meaningful sustainability comparison (Bernal *et al.*, 2024).

3.3 Lifecycle Cost Analysis and Total Cost Optimization

Integrated LCA and lifecycle cost (LCC) analysis reveals that UHPC solutions achieve cost reductions exceeding 40% despite higher initial material costs. The analysis compared UHPC basin designs with cantilever cast-in-situ walls to conventional reinforced concrete solutions and identified that reduced maintenance frequency provided substantial long-term cost savings (Summa *et al.*, 2023). For water tank applications, maintenance activities accounted for 91% of total lifecycle cost reduction achieved through UHPC implementation, with annual maintenance activities declining from multiple interventions to single annual inspections.

Economic analysis of HPC incorporating supplementary materials demonstrates that optimization considering targeted strength levels rather than prescriptive 28-day strength provides approximately 14% production cost savings, particularly for slag and pozzolan-based cements (Jesus *et al.*, 2025). Multi-objective

optimization algorithms identified optimal cement replacement levels ranging from 40-55%, balancing early-strength requirements with long-term durability and cost minimization (Aziz *et al.*, 2024). Material cost analysis across various SCM combinations revealed that binary and ternary blends typically cost 15-25% less than equivalent-strength conventional concrete when considering total lifecycle expenses including maintenance.

3.4 Machine Learning-Based Mix Design Optimization

Advanced machine learning models achieve exceptional predictive accuracy for HPC properties, with Random Forest algorithms achieving $R^2 = 0.97$ for compressive strength prediction and MLP networks reaching $R^2 = 0.96$ for porosity estimation (Parhi and Patro, 2025). XGBoost models specifically developed for sustainable concrete demonstrated superior performance, with R^2 values of 0.9689 for training datasets and 0.9632 for testing datasets, substantially outperforming conventional empirical models (Alkharisi and Dahish, 2025). These high-accuracy predictions enable confidence in mix design optimization results, reducing the necessity for extensive laboratory validation.

Optimization algorithms generating Pareto-optimal solutions identified mix designs providing 25% CO₂ emission reduction at 36 MPa compressive strength compared to baseline conventional concrete (K. *et al.*, 2026). The integration of SHAP analysis revealed that curing time and cement content represent the most influential parameters affecting strength prediction, with curing period demonstrating the highest positive impact on long-term properties (Alkharisi and Dahish, 2025). Feature importance analysis identified that while fly ash percentage influences compressive strength prediction by approximately 25%, cement content and curing time demonstrate greater relative importance, guiding practical engineering decision-making.

Table4:Machine LearningModel Performance andOptimization Results

Optimization Method	Strength	Prediction	Cost Reduction	CO ₂ Reduction
	(R ²)			
Random Forest	0.97		8-12%	15-20%

Optimization Method		Strength	Prediction	Cost Reduction	CO ₂ Reduction
		(R ²)			
XGBoost		0.9689		12-18%	20-25%
ANN		0.93		10-14%	18-22%
NSGA-II	Multi-	0.95		15-22%	25-30%
objective					

3.5 Regional Variations and Material Availability

Environmental impact assessment reveals substantial geographic variation in concrete sustainability profiles, driven primarily by electricity grid carbon intensity and local material availability. CLT and GLT production exhibits 52% higher carbon emissions outside Europe (167 kg CO₂-eq/m³) compared to European production (110 kg CO₂-eq/m³), primarily due to differences in wood species, manufacturing practices, and energy sources (Ijeoma *et al.*, 2025). Similarly, crushed dune sand availability in arid regions offers unique opportunity for sustainable concrete development with minimal environmental impact, while limestone powder sourcing varies significantly depending on regional geology and transportation distances.

Water footprint assessments demonstrate that concrete production and maintenance activities consume substantial water quantities, with implications for sustainability in water-stressed regions. Lifecycle assessment of green roof systems incorporating various material options revealed optimization pathways for simultaneously reducing heat transfer coefficients and minimizing carbon footprints through appropriate soil thickness selection and substrate composition (Wu *et al.*, 2025).

4. DISCUSSION

4.1 Integration of Sustainability Assessment into Design Practice

The evolution from prescriptive concrete design standards toward performance-based frameworks represents a fundamental shift enabling genuine optimization of sustainability (Aznav, 2025). Performance-based design methodologies permit engineers to specify desired service life, durability target, and environmental constraints, enabling computational algorithms to identify optimal

material combinations and structural configurations. This paradigm contrasts sharply with conventional approaches that specify concrete strength grade and prescriptive mix proportions, often resulting in over-designed structures with unnecessary environmental burden. The transition requires development of standardized performance metrics, reliable prediction models, and clear communication frameworks between designers, material suppliers, and construction teams.

4.2 Standardization and Testing Protocol Development

A critical gap in current HPC sustainability assessment involves the multiplicity of testing standards across different regions and applications. The RILEM TC 281-CCC analysis identified at least 17 different standards for carbonation testing alone, with significant variations in sample curing, pre-conditioning, exposure conditions, and depth determination methods (Bernal *et al.*, 2024). These variations substantially influence carbonation depth measurements and calculated carbonation coefficient values, compromising meaningful comparison of materials and design approaches across projects and jurisdictions. Development of globally harmonized testing protocols represents an urgent priority, as standardization would enable more confident prediction of long-term durability performance and more reliable comparison of environmental benefit across different concrete systems.

The assessment of electrical resistivity emerges as particularly promising for UHPC evaluation, demonstrating strong correlation with chloride migration and providing consistent differentiation among different HPC mixes. However, standardization of electrical resistivity testing procedures requires attention to electrode configuration, moisture conditions,

and temperature normalization to ensure reproducibility across laboratories. The continued evolution of non-destructive testing methods including ultrasonic pulse velocity, dynamic modulus measurement, and advanced imaging techniques offers additional assessment capabilities that complement conventional destructive testing approaches.

4.3 Circular Economy and Material Valorization

The integration of industrial waste streams and recycled materials into HPC represents a critical pathway toward circular economy implementation in construction. Fly ash, GGBFS, and silica fume represent coal combustion residues and steel manufacturing byproducts that would otherwise require disposal, creating both waste management and resource scarcity challenges. The valorization of these materials as supplementary cementitious materials converts waste streams into high-value construction components while simultaneously reducing environmental impact of concrete production. Current research demonstrates feasibility of incorporating 40-50% cement replacement with combined fly ash and slag, achieving superior durability performance while dramatically reducing embodied carbon.

Emerging waste streams including recycled concrete powder, glass powder, and eggshell powder demonstrate potential for further circular economy integration (Wilson *et al.*, 2019; Wang *et al.*, 2025) (Shah, Khoso, & Umali, 2026; Shah, Khoso, Iqbal, et al., 2026; Shah, Ullah, Khoso, & Umali, 2026; Shah, Ullah, Khoso, Iqbal, et al., 2026; Shah & Wahab, 2022). However, valorization of these materials requires development of reliable characterization methods to ensure consistency and predictability of performance. Life cycle assessment frameworks must expand beyond traditional material accounting to include avoided impacts from waste disposal, secondary material transportation optimization, and end-of-life recycling potential. The integration of geographic information systems (GIS) and remote sensing technologies enables spatial inventory management of waste streams, optimizing material logistics and minimizing transportation distances.

4.4 Technology Integration and Digital Innovation

The convergence of advanced materials, digital technologies, and artificial intelligence provides unprecedented capacity for sustainability optimization in concrete design (Aznaw, 2025). Building Information Modelling enables integrated assessment of material, structural, and operational environmental impacts across building lifecycles. Digital twins permit real-time performance monitoring, enabling early detection of durability issues and optimized maintenance scheduling. Machine learning algorithms trained on comprehensive datasets identify optimal mix designs, predict long-term performance with high accuracy, and enable inverse design approaches that specify desired sustainability targets while solving for required material compositions.

The development of comprehensive, globally diverse datasets of HPC mix designs and performance outcomes represents a critical prerequisite for effective machine learning application. A consolidated dataset of 2188 UHPC mix designs from 168 publications (Malik *et al.*, 2025) demonstrates the feasibility of developing substantial experimental databases that support robust model development. However, continued expansion and refinement of these datasets, including incorporation of regional variations in material properties and long-term performance outcomes, remains necessary to ensure model reliability across diverse geographic and climatic contexts.

4.5 Resilience and Long-Term Durability

Performance-based design frameworks increasingly integrate resilience considerations alongside traditional durability assessment, recognizing that infrastructure systems must maintain functionality despite exposure to evolving environmental stresses. Climate change implications including increased exposure to extreme weather events, elevated temperatures, and modified chloride and sulfate regimes necessitate concrete systems capable of maintaining structural integrity and serviceability across extended lifecycles (Z, C and J., 2024). Research examining combined effects of stress and carbonation reveals

significant gaps in current knowledge regarding long-term impacts of complex loading conditions on durability performance.

The development of high-resilience materials incorporating engineered cementitious composites (ECCs), fiber reinforcement, and advanced admixtures enables structures to accommodate cracking and degradation mechanisms while maintaining load-bearing capacity. These materials demonstrate particular value in seismic-prone regions and aggressive environmental exposures, where conventional concrete exhibits accelerated deterioration. The integration of self-healing mechanisms, either through continued pozzolanic reactions or embedded healing agents, offers emerging technology for extending structural service life and reducing maintenance frequency.

4.6 Research Gaps and Future Directions

Despite substantial advances in HPC sustainability assessment, critical research gaps persist requiring future investigation. First, long-term performance data under realistic service conditions remain limited, with most durability assessments conducted through accelerated testing procedures that may not accurately represent actual environmental interactions. Second, the development of standardized testing protocols that meaningfully differentiate HPC performance while remaining practical for routine implementation requires continued collaboration among researchers, standards organizations, and engineering practitioners. Third, the integration of sustainability considerations into building codes and design standards remains incomplete in many jurisdictions, limiting adoption of optimized design approaches.

Fourth, the environmental impacts associated with new materials and admixtures warrant more comprehensive assessment, as emerging compounds may provide performance benefits while introducing novel environmental concerns. Finally, the quantification of resilience and adaptation capacity in formal sustainability frameworks remains inadequately developed, despite growing recognition of these

factors' importance in determining infrastructure value across extended lifecycles.

5. CONCLUSION AND RECOMMENDATIONS

5.1 Key Findings and Synthesis

This comprehensive review reveals that high-performance concrete possesses substantial potential to advance infrastructure sustainability through multiple complementary mechanisms. First, the integration of supplementary cementitious materials achieves carbon footprint reductions of 25-40% through direct cement displacement, with additional benefits emerging from extended service life and reduced maintenance requirements. Optimally designed concrete incorporating 25-35% SCM replacement by cement weight achieves total lifecycle environmental impact reductions of 60-80% compared to conventional solutions, exceeding reductions achievable through any single intervention. Second, advanced durability assessment methodologies enable reliable prediction of service life and optimization of maintenance scheduling, substantially improving environmental performance by extending structural functionality and minimizing repair interventions.

Third, the convergence of computational technologies and material science enables data-driven optimization of concrete mixes that simultaneously achieve structural performance targets, economic feasibility, and environmental sustainability objectives. Machine learning models achieving prediction accuracy above $R^2 = 0.96$ provide confidence in mix design optimization while substantially reducing laboratory testing requirements. Fourth, the transition from prescriptive standards toward performance-based design frameworks permits genuine engineering optimization rather than compliance with predetermined specifications, enabling customization of concrete properties to specific project requirements and environmental contexts.

5.2 Implementation Recommendations

To advance practical implementation of sustainable HPC in construction practice, the

following recommendations merit priority consideration:

Standardization and Protocol Development:

International collaborative efforts should accelerate development of globally harmonized testing standards for concrete durability assessment, with particular emphasis on carbonation and chloride penetration testing procedures. Electrical resistivity measurement standardization deserves priority due to its demonstrated utility for UHPC evaluation and potential to provide rapid, non-destructive assessment of material quality.

Building Code Integration: Design standards and building codes should evolve toward explicit performance-based specifications incorporating service life requirements, durability targets, and environmental sustainability criteria. This evolution should include development of material efficiency standards that account for functional performance per unit environmental impact, encouraging optimization rather than simple prescriptive compliance.

Data Management and Digital Infrastructure:

Continued development of comprehensive, openly accessible databases of HPC mix designs, performance outcomes, and sustainability metrics should receive substantial research investment. These databases provide essential foundations for machine learning model development and enable identification of robust material combinations performing reliably across diverse geographic and environmental contexts.

Material Valorization Policy:

Government policies should incentivize waste-derived material integration through preferential pricing structures, tax incentives, or procurement specifications favoring materials incorporating industrial by-products. Regulatory frameworks should harmonize characterization standards for SCMs across jurisdictions, reducing barriers to inter-regional

material trade and enabling optimization of material logistics.

Research Priority Areas: Future research should emphasize long-term field performance monitoring, particularly in diverse environmental exposures and climatic regions. Systematic investigation of emerging waste streams and byproduct materials should continue, with particular attention to developing characterization methodologies ensuring performance predictability. Integration of resilience frameworks into sustainability assessment represents an urgent priority, as infrastructure systems must maintain functionality despite evolving environmental stresses.

5.3 Concluding Remarks

The sustainability assessment of high-performance concrete structures reflects a maturation of both material science and environmental assessment methodologies, enabling engineering practice to advance beyond traditional performance-focused design toward holistic consideration of economic, environmental, and social factors. The substantial body of research synthesized in this review demonstrates that optimized HPC systems, incorporating appropriate supplementary materials and designed through performance-based frameworks, can achieve significant environmental benefits while maintaining or exceeding structural performance compared to conventional construction approaches. Continued advancement requires sustained collaboration among researchers, practitioners, standards organizations, and policymakers to overcome remaining technical challenges, standardize assessment procedures, and integrate sustainability considerations into engineering education and professional practice. The convergence of advanced materials, computational technologies, and performance-based design philosophy positions high-performance concrete as a foundation technology for building sustainable, resilient infrastructure systems capable of supporting urban societies while respecting planetary environmental boundaries.

REFERENCES

- Abdullah, A.F. *et al.* (2025) 'Enhancing the sustainability of concrete mixes utilizing supplementary cementitious materials in renewable energy buildings', *Engineering, Technology & Applied Science Research* [Preprint]. doi:10.48084/etasr.12936.
- Adamu, M. *et al.* (2025) 'Multicriteria-based optimization and multi-variable non-linear regression analysis of concrete containing blends of nano date palm ash and eggshell powder as cementitious materials', *Nanotechnology Reviews* [Preprint]. doi:10.1515/ntrev-2025-0141.
- Akbar, G. *et al.* (2025) 'Sustainable innovations in ultra-high-performance concrete for smart and resilient structures: A survey', *European Journal of Applied Science, Engineering and Technology* [Preprint]. doi:10.59324/ejaset.2025.3(5).15.
- Aktas, K.O. *et al.* (2025) 'Evaluation of space efficiency, structural systems, material applications, and design of high-rise structures in south korea', *Highlights of Sustainability* [Preprint]. doi:10.54175/hsustain4040016.
- Ali, H.H.M. (2023) 'Advances in high-performance concrete: A comprehensive review of materials, design, and applications', *KHWARIZMIA* [Preprint]. doi:10.70470/khwarizmia/2023/013.
- Alkharisi, M.K. and Dahish, H.A. (2025) 'Tensile strength of RA concrete containing supplementary cementitious materials and polypropylene fibers utilizing machine learning with GUI', *Buildings* [Preprint]. doi:10.3390/buildings15244473.
- Al-Omari, O. *et al.* (2023) 'Evaluating carbon footprint in the life cycle design of residential concrete structures in Jordan', *Civil Engineering Journal* [Preprint]. doi:10.28991/cej-2023-09-07-07.
- Avet, F. *et al.* (2022) 'Report of RILEM TC 267-TRM phase 2: Optimization and testing of the robustness of the R3 reactivity tests for supplementary cementitious materials', *Materials and Structures* [Preprint]. doi:10.1617/s11527-022-01928-6.
- Aziz, A. *et al.* (2024) 'Enhancing sustainability in self-compacting concrete by optimizing blended supplementary cementitious materials', *Scientific Reports* [Preprint]. doi:10.1038/s41598-024-62499-w.
- Aznaw, G. (2025) 'Meta-analysis of emerging trends in sustainable structural engineering: Integrating high-performance materials, digital design, and resilient infrastructure', *Research and Innovation* [Preprint]. doi:10.11648/j.ri.20250101.22.
- Babar, M.U. (2026) 'Advancing seismic resilience through sustainable structural solutions: A review of material and analytical innovations in RC design', *Fusion Journal of Engineering and Sciences* [Preprint]. doi:10.64615/fjes...2026.84.
- Bahmani, H., Mostafaei, H. and Mostofinejad, D. (2025) 'Review of energy dissipation mechanisms in concrete: Role of advanced materials, mix design, and curing conditions', *Sustainability* [Preprint]. doi:10.3390/su17156723.
- Bernal, S. *et al.* (2024) 'Report of RILEM TC 281-CCC: A critical review of the standardised testing methods to determine carbonation resistance of concrete', *Materials Structure* [Preprint]. doi:10.1617/s11527-024-02424-9.
- Bijeljić, J. and Niederleithinger, E. (2025) 'CONCRETE PERFORMANCE ASSESSMENT BASED ON GAS PERMEABILITY TESTING', *Journal of the Faculty of Civil Engineering and Architecture* [Preprint]. doi:10.62683/zrgaf41.2.

- Bradshaw, J. et al. (2025) 'Emerging insights into the durability of 3D-printed concrete: Recent advances in mix design parameters and testing', *Designs* [Preprint]. doi:10.3390/designs9040085.
- Chu, S. (2021) 'Development of infilled cementitious composites (ICC)', *Composite structures* [Preprint]. doi:10.1016/J.COMPSTRUCT.2021.113885.
- Cordoba, G.P. and Irassar, E. (2023) 'Carbon footprint of reinforced concrete columns with and without supplementary cementitious materials', *The International Journal of Life Cycle Assessment* [Preprint]. doi:10.1007/s11367-023-02182-w.
- Farouk, A.I.B. and Haruna, S. (2020) 'Evaluation of bond strength between ultra-high-performance concrete and normal strength concrete: An overview', *Jurnal Kejuruteraan* [Preprint]. doi:10.17576/jkukm-2020-32(3)-04.
- Firman, R. et al. (2025) 'Optimization of high early-strength concrete mix design for structural applications in the BJ. Habibie stadium construction project', *Civilla : Jurnal Teknik Sipil Universitas Islam Lamongan* [Preprint]. doi:10.30736/cvl.v10i2.1424.
- Ganieva, K. et al. (2024) 'Enhancing machine tool housing design through ultra high-performance concrete', *Applied Mechanics and Materials* [Preprint]. doi:10.4028/p-5799sF.
- Garg, M. and Roy, S. (2026) 'Life cycle emission analysis and case specific mitigation strategies for hostel buildings in the lower himalayan region.', *International journal of research and scientific innovation* [Preprint]. doi:10.51244/ijrsi.2026.1305000090.
- Gedam, B.A. et al. (2019) 'Improved durability of concrete using supplementary cementitious materials'. doi:10.18552/2019/idsmt5151.
- Gopu, G. (2025) 'AI-driven optimization of eco-friendly concrete mix design using industrial by-products', *2025 World Conference on Cutting-Edge Science and Technology (WCCEST)* [Preprint]. doi:10.1109/WCCEST66994.2025.11389881.
- Guo, J. et al. (2024) 'Mechanical properties and mesoscopic numerical simulation of local weakening in high-performance concrete after 10 years of alkali solution immersion', *Buildings* [Preprint]. doi:10.3390/buildings14071965.
- Habibi, A., Ramezani pour, A. and Mahdikhani, M. (2021) 'RSM-based optimized mix design of recycled aggregate concrete containing supplementary cementitious materials based on waste generation and global warming potential'. doi:10.1016/J.RESCONREC.2021.105420.
- Hamada, H.M. and Abed, F. (2024) 'Optimization and modeling of 7-day ultra-high-performance concrete comprising desert sand and supplementary cementitious materials using response surface methodology', *Buildings* [Preprint]. doi:10.3390/buildings14072058.
- Hamdi, M.S., Nahhab, A.H. and Kadhim, M.J. (2026) 'Optimization and prediction of lightweight self-compacting concrete mix design using taguchi optimization method', *IOP Conference Series: Earth and Environment* [Preprint]. doi:10.1088/1755-1315/1644/1/012068.
- Hao, Z. et al. (2024) 'Strength and durability of high-performance preplaced aggregate concrete for rapid pavement repair', *International Journal of Pavement Engineering* [Preprint]. doi:10.1080/10298436.2024.2446388.

- Hasnat, S. and Manzur, T. (2025) 'Sustainability assessment of marine RC structures containing mid to high volume supplementary cementitious materials', *Sustainable Engineering Materials* [Preprint]. doi:10.54113/j.suem.2025.000007.
- Hassan, M. and Aljalawi, N. (2025) 'Performance evaluation of SIFCON incorporating waste materials and hybrid fibers: A study on durability and mechanical properties', *Engineering, Technology & Applied Science Research* [Preprint]. doi:10.48084/etasr.10365.
- Hoque, K.N. and Presuel-Moreno, F. (2025) 'Long-term corrosion behavior of reinforced concrete: Impact of supplementary cementitious materials and reservoir size under accelerated chloride ingress', *Construction Materials* [Preprint]. doi:10.3390/constrmater5020033.
- Ijeoma, M.W. et al. (2025) 'Assessing the energy demand, carbon footprint and other environmental impacts from mass timber production: A critical review and meta-analysis', *Environmental Research Communications* [Preprint]. doi:10.1088/2515-7620/ae1810.
- Ilgin, H.E. et al. (2024) 'Life cycle assessment of an office building in finland using a custom assessment tool', *Buildings* [Preprint]. doi:10.3390/buildings14071944.
- Javidmehr, S. and Empelmann, M. (2021) 'Shear bond between ultra-high performance fibre reinforced concrete overlays and normal strength concrete substrates', *Sustainability* [Preprint]. doi:10.3390/SU13158229.
- Jesus, W.S. de et al. (2025) 'Leveraging delayed strength gains in supplementary cementitious material concretes: Rethinking mix design for enhanced cost efficiency and sustainability', *Journal of Composites Science* [Preprint]. doi:10.3390/jcs9030110.
- Jia, Y. (2024) 'The application of high-performance concrete in building structures and analysis of its effects', *Journal of Civil Engineering and Urban Planning* [Preprint]. doi:10.23977/jceup.2024.060219.
- K., L. et al. (2026) 'Sustainable concrete mix design using bio-waste materials and metaheuristic algorithms optimization', *2026 International Conference on Sustainable and Futuristic Technologies (ICSFT)* [Preprint]. doi:10.1109/ICSFT67370.2026.11566176.
- Kamionka, L. (2022) 'Sustainable design in terms of use of environmentally friendly materials', *Środowisko Mieszkaniowe* [Preprint]. doi:10.4467/25438700sm.22.031.17154.
- Kandaswamy, S. et al. (2025) 'Durability of high-performance concrete at high temperatures: Effects of water-binder ratios and use of silica fume', *Matéria* [Preprint]. doi:10.1590/1517-7076-rmat-2024-0704.
- Kara, S., Erdem, S. and Lezcano, R. (2021) 'MgO-based cementitious composites for sustainable and energy efficient building design', *Sustainability* [Preprint]. doi:10.3390/su13169188.
- Kayali, O., Haque, M. and Khatib, J.M. (2008) 'Sustainability and emerging concrete materials and their relevance to the middle east'. doi:10.2174/1874836800802010103.
- Mahmood, M., Alias, A. and Hasan, K. (2026) 'A bibliometric and technical review of supplementary cementitious materials for 3D concrete printing: Research trends, current status, challenges, and future directions', *The Arabian journal for science and engineering* [Preprint]. doi:10.1007/s13369-026-11117-0.
- Malik, U.J. et al. (2025) 'A global dataset of UHPC mix designs with supplementary cementitious materials and nano additives', *Data in Brief* [Preprint]. doi:10.1016/j.dib.2025.112179.

- Mou, X. *et al.* (2025) 'Research on fatigue performance and life prediction of steel-concrete composite structural materials', *Matéria* [Preprint]. doi:10.1590/1517-7076-rmat-2025-0072.
- Mousa, A.A., Abed, J. and Shukur, M.H. (2025) 'Effect of supplementary cementitious materials on corrosion resistance of reinforced concrete', *Civil and Environmental Engineering* [Preprint]. doi:10.2478/cee-2025-0080.
- Nandurkar, B. *et al.* (2025) 'Optimization and predictive performance of fly ash-based sustainable concrete using integrated multitask deep learning framework with interpretable machine learning techniques', *Scientific Reports* [Preprint]. doi:10.1038/s41598-025-16678-y.
- Nguyen, H. *et al.* (2022) 'A review on current direct and indirect testing methods as high-effective techniques in the evaluation of self-healing ability in concrete', *JOURNAL OF MATERIALS & CONSTRUCTION* [Preprint]. doi:10.54772/jomc.v12i01.326.
- Parhi, S.K. and Patro, S.K. (2025) 'Data-driven prediction and intelligent optimization of strength, porosity and cost of concrete with supplementary cementitious materials', *Journal of Structural Integrity and Maintenance* [Preprint]. doi:10.1080/24705314.2025.2567084.
- Pillay, D.L. *et al.* (2020) 'A review of the engineering properties of metakaolin based concrete: Towards combatting chloride attack in coastal/marine structures', *Advance in Civil Engineering* [Preprint]. doi:10.1155/2020/8880974.
- Raouffard, M. *et al.* (2025) 'Fostering sustainability in conventional reinforced concrete building structures: Effective measures in kobe port museum building', *IABSE Reports* [Preprint]. doi:10.2749/tokyo.2025.1734.
- Rennani, F.Z. *et al.* (2025) 'Enhancement of high-performance concrete properties with crushed dune sand addition: A sustainable approach for desert regions', *Materials Science* [Preprint]. doi:10.2478/msp-2025-0036.
- Sadrossadat, E. and Basarir, H. (2019) 'An evolutionary-based prediction model of the 28-day compressive strength of high-performance concrete containing cementitious materials', *Advances in Civil Engineering Materials* [Preprint]. doi:10.1520/ACEM20190016.
- Saladi, N. *et al.* (2023) 'Assessing durability properties of ultra-high performance concrete-class materials', *Materials and Structures* [Preprint]. doi:10.1617/s11527-023-02244-3.
- Shahroodi, S.Y.H. (2024) 'Improvement of seismic performance of concrete structures using magnetized concrete: An empirical study', *Discover Civil Engineering* [Preprint]. doi:10.1007/s44290-024-00073-z.
- Singh, A., Vaddy, P. and Biligiri, K.P. (2020) 'Quantification of embodied energy and carbon footprint of pervious concrete pavements through a methodical lifecycle assessment framework'. doi:10.1016/j.resconrec.2020.104953.
- Singh, Er.M., Dhir, Dr.V. and Simran, Er. (2025) 'A multi-method AI framework for the sustainable optimization of concrete mix designs using industrial and agricultural waste: A comprehensive review', *International research journal of innovations in engineering and technology* [Preprint]. doi:10.47001/irjiet/2025.909012.
- Soeda, M., Yamato, T. and Emoto, Y. (1999) 'Frost durability of high-performance concrete incorporating slag or silica fume', *High Performance Concrete* [Preprint]. doi:10.14359/5569.
- Summa, D. *et al.* (2023) 'A holistic life cycle design approach to enhance the sustainability of concrete structures', *Structural Concrete* [Preprint]. doi:10.1002/suco.202300645.

- Sundin, M., Hedlund, H. and Ćwirzeń, A. (2023) 'Eco-concrete in high temperatures', *Materials* [Preprint]. doi:10.3390/ma16124212.
- Shah, Q., Ullah, I., Khoso, W.A., Iqbal, F., et al. (2026) "Explainable and comparative machine learning models for punching shear prediction in reinforced concrete flat slabs," *Multiscale and Multidisciplinary Modeling, Experiments and Design*, 9(1), p. 146. Available at: <https://doi.org/10.1007/s41939-026-01219-5>.
- Shah, Q., Khoso, W.A., et al. (2026) "Explainable ensemble learning framework for bond strength prediction in 3D printed concrete structures," *Discover Artificial Intelligence* [Preprint]. Available at: <https://doi.org/10.1007/s44163-026-01925-6>.
- Shah, Q., Ullah, I., Khoso, W.A. and Umali, M. (2026) "Interpretable machine learning for predicting reinforced concrete beam column joint shear strength," *Discover Civil Engineering*, 3(1), p. 153. Available at: <https://doi.org/10.1007/s44290-026-00539-2>.
- Shah, Q., Khoso, W.A. and Umali, M. (2026) "Machine learning based prediction and analysis of bond strength between steel reinforcement and geopolymers concrete under cyclic loading for seismic applications: a review," *Journal of Infrastructure Preservation and Resilience* [Preprint]. Available at: <https://doi.org/10.1186/s43065-026-00208-9>.
- Shah, Q. and Wahab, H. (2022) *EXPERIMENTAL AND NUMERICAL INVESTIGATION OF LOADED REINFORCED CONCRETE BEAM USING FINITE ELEMENT ANALYSIS*. Available at: <https://doi.org/10.13140/RG.2.2.20658.57283>.
- Tushar, Q. et al. (2025) 'Carbon footprint and uncertainties of geopolymers concrete production: A comprehensive life cycle assessment (LCA)', *C++ Conference* [Preprint]. doi:10.3390/c11030055.
- Vaidevi, C., Kala, T. and Kalaiyarrasi, A. (2020) 'Mechanical and durability properties of self-compacting concrete with marble fine aggregate', *Materials Today: Proceedings* [Preprint]. doi:10.1016/j.matpr.2019.11.019.
- Vaitkevicius, V., Šerelis, E. and Rudžionis, Ž. (2012) 'NONDESTRUCTIVE TESTING OF ULTRA-HIGH PERFORMANCE CONCRETE TO EVALUATE FREEZE-THAW RESISTANCE'. doi:10.5755/J01.MECH.18.2.1565.
- Voß, S., Schmidt, B. and Oettel, V. (2025) 'Fatigue resistance of concrete: Influence of time-dependent scattering of compressive strength', *Materials Structure* [Preprint]. doi:10.1617/s11527-024-02517-5.
- Wang, S. et al. (2025) 'Recycled concrete powder surface modification via graphene oxide for high performance, low carbon and cost-effective cement paste development.', *Environmental Research* [Preprint]. doi:10.1016/j.envres.2025.123584.
- Wei, W. et al. (2025) 'Energy consumption and carbon emissions in asphalt pavement construction: A lifecycle assessment of a modular approach', *Materials Science* [Preprint]. doi:10.5755/j02.ms.41184.
- Wilson, W. et al. (2019) 'Micro-chemo-mechanical features of ultra-high performance glass concrete (UHPGC)'. doi:10.1016/j.tafmec.2019.102373.
- Wu, D. et al. (2025) 'Optimization of heat transfer coefficient in green roof modules based on life cycle carbon emissions', *Journal of Asian Architecture and Building Engineering* [Preprint]. doi:10.1080/13467581.2025.2472715.

Z, L., C, S. and J., Q. (2024) 'Coupling effects of stress and carbonation on concrete durability: A review.'
doi:10.3390/ma17225438.

Zaki, A. *et al.* (2025) 'Corrosion evaluation on fly ash and silica fume concrete using NDT methods', *International Islamic University Malaysia Engineering Journal* [Preprint].
doi:10.31436/iiumej.v26i3.3606.

Zhao, H. *et al.* (2025) 'Development, challenges, and applications of concrete coating technology: Exploring paths to enhance durability and standardization', *Coatings* [Preprint].
doi:10.3390/coatings15040409.

Zhou, Y. *et al.* (2025) 'Multi-objective optimization design of straw concrete mix proportions based on the NSGA-II algorithm', 2025 6th *International Journal of Conference on Computer Engineering and Intelligent Control (ICCEIC)* [Preprint].
doi:10.1109/ICCEIC67916.2025.11308994.