

INORGANIC SYNTHESIS AND CHARACTERIZATION OF TRANSITION-METAL NANOMATERIALS FOR ADVANCED ENERGY STORAGE

Naeem Ullah Khan^{*1}, Muhammad Adnan², Bilal Hussain³

^{*1}Department of Chemistry, University of Mianwali

²Department of Chemistry, National College of Business Administration & Economics

³Department of Chemistry, Bahaudin Zakaria University, Multan

^{*1}samarniaxi2313@gmail.com, ²adnanric204@gmail.com, ³bilalhussain18774@gmail.com

³ORCID: 0009-0007-0794-656X

DOI: <https://doi.org/10.5281/zenodo.22953714>

Keywords

Transition-metal nanomaterials;
Inorganic synthesis;
Nanostructured electrodes; Energy
storage; Supercapacitors;
Batteries; Electrochemical
performance

Article History

Received: 01 June 2026

Accepted: 23 August 2026

Published: 25 September 2026

Copyright @Author

Corresponding Author: *

Naeem Ullah Khan

Abstract

The increasing demand for high-performance and sustainable energy-storage technologies has intensified the need for advanced electrode materials capable of delivering high energy density, rapid charge-discharge rates, long cycle life, and structural stability. Conventional electrode materials often suffer from limited electrical conductivity, sluggish ion transport, and capacity degradation during repeated cycling. This review examines the inorganic synthesis, structural characterization, electrochemical properties, and energy-storage applications of transition-metal nanomaterials, with particular emphasis on transition-metal oxides, sulfides, nitrides, hydroxides, and mixed-metal compounds. Major synthesis strategies, including sol-gel, co-precipitation, hydrothermal/solvothermal, combustion, electrodeposition, sonochemical, and green synthesis routes, are critically discussed in relation to particle size, morphology, crystallinity, porosity, defect chemistry, and surface area. Characterization approaches involving X-ray diffraction, electron microscopy, spectroscopy, surface-area analysis, and electrochemical techniques are evaluated for establishing structure-property relationships. Recent research demonstrates that nanoscale engineering can increase electrochemically active surface area, shorten ion-diffusion pathways, improve charge-transfer kinetics, and provide abundant redox-active sites. However, aggregation, structural instability, poor intrinsic conductivity, volume changes, synthesis reproducibility, and scale-up remain significant challenges. Future progress depends on rational defect engineering, hierarchical architectures, conductive composites, green synthesis, and operando characterization. Overall, transition-metal nanomaterials offer substantial potential for next-generation batteries, supercapacitors, and hybrid energy-storage devices, provided that laboratory-scale electrochemical performance is translated into practical device-level durability and scalable manufacturing.

INTRODUCTION

The rapid expansion of electric transportation, portable electronics, renewable-energy systems, and grid-connected technologies has increased the requirement for efficient electrochemical energy-storage systems. Modern energy-storage devices must simultaneously satisfy several demanding requirements, including high energy density, high power density, rapid charging, long operational lifetime, safety, affordability, and environmental sustainability. Lithium-ion batteries have become dominant in portable electronics and electric vehicles, while supercapacitors provide exceptionally rapid charge-discharge and high power delivery. Nevertheless, limitations associated with electrode capacity, ion transport, conductivity, cycling stability, and material cost continue to motivate the search for advanced electrode materials.

Nanomaterials have become particularly important because reducing material dimensions to the nanoscale can modify transport, surface, structural, and electrochemical properties. Transition-metal nanomaterials are especially attractive because transition metals possess multiple oxidation states and can participate in reversible or quasi-reversible redox reactions. Consequently, transition-metal oxides (TMOs), sulfides, nitrides, hydroxides, phosphides, and mixed-metal compounds have been extensively investigated as electrodes for batteries and supercapacitors. Recent literature emphasizes that the morphology, porosity, crystal structure, defects, and composition of these materials strongly influence electrochemical behavior.

Transition-metal oxides such as MnO_2 , NiO , Co_3O_4 , Fe_2O_3 , CuO , TiO_2 , and RuO_2 possess diverse chemical and electronic characteristics. Their electrochemical activity can originate from surface redox reactions, ion insertion/extraction, or conversion reactions depending on the material and storage system. Binary and ternary transition-metal compounds can provide additional advantages because combining different metal centers may increase the number

of redox-active sites and modify electronic structure. Recent reviews indicate that micro- and nanostructured binary transition-metal oxides are receiving substantial attention for lithium-ion battery anodes because their architectures can improve reaction kinetics and accommodate structural changes.

Transition-metal sulfides have emerged as another important class. Compared with many oxides, sulfides can provide favorable electronic conductivity and rich redox chemistry. Recent studies identify NiCo_2S_4 , CoMoS_4 , and other binary or ternary sulfides as promising candidates for high-performance supercapacitor electrodes. However, sulfides can still experience inadequate cycling stability, limited active-site accessibility, and structural changes during repeated electrochemical operation.

The importance of synthesis cannot be separated from the performance of these materials. Different inorganic synthesis approaches produce different particle sizes, morphologies, crystallographic phases, surface areas, pore structures, and defect concentrations. Hydrothermal synthesis, for example, can produce highly controlled nanostructures with relatively high surface area, whereas sol-gel and co-precipitation methods provide attractive opportunities for compositional control and relatively simple processing.

Therefore, the present review examines the relationship between **inorganic synthesis** → **nanostructure** → **characterization** → **electrochemical properties** → **energy-storage performance**. Particular attention is given to recent research published during 2023–2026 and to the challenges that must be addressed before transition-metal nanomaterials can move from laboratory research toward practical energy-storage technologies.

Transition-Metal Nanomaterials for Energy Storage

Transition metals are characterized by partially filled d-orbitals and variable oxidation states. These characteristics make them suitable for electrochemical reactions in which electrons and

ions are reversibly transferred. At the nanoscale, their behavior can differ substantially from that of bulk materials because surface atoms constitute a much larger fraction of the total material.

For energy-storage applications, desirable characteristics include:

1. high electrochemical activity;
2. large accessible surface area;
3. rapid electron transport;
4. short ion-diffusion pathways;
5. structural stability;
6. high density of redox-active sites;
7. suitable electrical conductivity;
8. controllable porosity;
9. chemical compatibility with the electrolyte; and scalable synthesis.

Nanostructuring can address several of these requirements simultaneously. Smaller particles reduce diffusion distances, while porous architectures increase electrolyte accessibility. Nanowires, nanosheets, nanorods, hollow spheres, nanoflowers, and three-dimensional hierarchical structures can create continuous pathways for electron and ion transport.

Recent research on emerging energy-storage nanomaterials has increasingly focused on structure-property relationships rather than simply reporting high specific capacitance or capacity. Surface area, pseudocapacitance, structural disorder, architecture, and durability must be considered together when evaluating an electrode.

Transition-Metal Oxides

Transition-metal oxides constitute one of the most extensively investigated groups of electrode materials. MnO_2 , NiO , Co_3O_4 , Fe_2O_3 , CuO , TiO_2 , and RuO_2 have all demonstrated potential for electrochemical energy storage.

MnO_2 is attractive because of its abundance, relatively low cost, multiple polymorphs, and favorable redox activity. However, its relatively poor intrinsic electrical conductivity can restrict rate capability. Nanostructuring, conductive composites, defect engineering, and mixed-metal

architectures have therefore been employed to improve its electrochemical performance.

NiO provides high theoretical charge-storage capacity and is capable of reversible redox reactions. Nevertheless, conductivity and structural stability remain important concerns. Co_3O_4 similarly exhibits attractive redox characteristics and can participate in conversion reactions in battery systems and Faradaic reactions in supercapacitors.

RuO_2 has historically been recognized for excellent pseudocapacitive behavior, although the high cost and limited availability of ruthenium restrict large-scale applications. Consequently, contemporary research increasingly investigates less expensive alternatives and mixed-metal systems.

A 2025 review of transition-metal-based supercapacitor electrodes emphasizes that TMOs such as MnO_2 , NiO , ZnO , Co_3O_4 , vanadium oxides, and RuO_2 continue to receive attention because their oxidation-state flexibility enables Faradaic charge storage.

Transition-Metal Sulfides

Transition-metal sulfides are attractive because sulfur generally produces materials with favorable electronic properties and strong redox activity. Binary and ternary sulfides can offer greater compositional flexibility than single-metal compounds.

Examples include NiS , CoS , FeS , MoS_2 , NiCo_2S_4 , and other multicomponent sulfides. In supercapacitors, these materials can support rapid Faradaic reactions and high charge-storage capability.

The major problem is that high initial electrochemical performance does not necessarily translate into long-term stability. Structural reconstruction, dissolution, oxidation, volume changes, and incomplete utilization of active sites can cause performance deterioration.

Recent research therefore emphasizes sulfur-vacancy engineering, heteroatom doping, carbon integration, and hierarchical morphology as strategies for improving conductivity and durability.

Transition-Metal Hydroxides

Transition-metal hydroxides, particularly $\text{Ni}(\text{OH})_2$, $\text{Co}(\text{OH})_2$, and layered double hydroxides, are important pseudocapacitive materials. Their layered structures can facilitate electrolyte interaction and redox reactions.

However, hydroxide electrodes may suffer from conductivity limitations. Integration with graphene, carbon nanotubes, MXenes, or porous carbon can establish conductive networks and improve electron transport.

Transition-Metal Nitrides and Phosphides

Transition-metal nitrides combine metallic conductivity with electrochemical activity. Materials such as TiN , VN , Mo_2N , and related compounds have attracted interest for high-rate supercapacitors. Recent reviews have examined zero-, one-, two-, and three-dimensional nitride architectures, highlighting the relationship between structural dimensionality and electrochemical behavior.

Transition-metal phosphides are also being explored because their electronic structures can support rapid charge transfer. Their integration with carbonaceous substrates and other nanomaterials can further enhance electrochemical properties.

Inorganic Synthesis Strategies

The synthesis route determines the physicochemical characteristics of transition-metal nanomaterials. Parameters such as precursor concentration, pH, temperature, reaction time, solvent, reducing environment, calcination temperature, and surfactant concentration can influence nucleation and crystal growth.

Sol-Gel Method

The sol-gel method is based on controlled hydrolysis and condensation of molecular precursors, followed by gel formation, drying, and thermal treatment.

Its major advantages include:

- relatively good compositional homogeneity;
- controllable particle size;
- low-temperature chemical processing;
- suitability for mixed-metal oxides; and

- relatively simple incorporation of dopants.

However, drying and calcination may cause particle aggregation and grain growth. Therefore, optimization of heating rate and precursor chemistry is important.

Co-Precipitation

Co-precipitation is widely used for producing transition-metal oxides and hydroxides. Metal salts are dissolved in a suitable solvent and precipitated through pH adjustment or addition of a precipitating agent. The technique is attractive because it is inexpensive and relatively easy to scale. It is also suitable for preparing mixed-metal compositions. In sodium-ion battery research, for example, co-precipitation has been examined for producing layered transition-metal oxide cathode precursors while considering scale-up and hydrodynamic factors.

Nevertheless, uncontrolled precipitation can produce broad particle-size distributions and compositional inhomogeneity. Continuous control of pH, temperature, mixing, and feed rate is therefore essential.

Hydrothermal and Solvothermal Synthesis

Hydrothermal synthesis is among the most useful methods for producing transition-metal nanostructures. Reactions occur in sealed vessels at elevated temperature and pressure, allowing controlled nucleation and crystal growth. The method can generate nanorods, nanowires, nanosheets, hollow structures, and hierarchical architectures. A recent review of wet-chemical metal oxide synthesis identifies hydrothermal synthesis as particularly useful for producing nanomaterials with high surface area, which can improve electrochemically accessible surface area. Solvothermal synthesis follows similar principles but uses organic solvents rather than water. Solvent selection can modify reaction kinetics, morphology, and surface chemistry.

Sonochemical Synthesis

Sonochemical synthesis uses ultrasonic irradiation to generate localized high-temperature and high-pressure conditions through acoustic cavitation. These conditions can accelerate

nucleation and promote relatively small nanoparticles. The method is useful when controlling particle size and preventing excessive aggregation. However, energy consumption, process uniformity, and scale-up require careful consideration.

Combustion Synthesis

Combustion methods use exothermic reactions between oxidizing and reducing components to produce oxide nanoparticles. They can generate high-purity powders rapidly and are potentially suitable for large-scale production. However, the high local temperatures generated during combustion can cause uncontrolled grain growth. The fuel-to-oxidizer ratio therefore needs careful optimization.

Electrodeposition

Electrodeposition is especially useful when active materials are intended to be directly grown on conductive substrates. This approach can reduce the requirement for polymer binders and conductive additives. Directly grown nanostructures can provide improved contact between the active material and current collector. Electrodeposition is particularly attractive for flexible and micro-scale devices.

Green Synthesis

Sustainable synthesis has become increasingly important. Plant extracts, microorganisms, biomass, and agro-industrial waste can provide reducing, stabilizing, or complexing agents for nanoparticle formation.

A 2024 review reports that green nanoparticle synthesis can reduce environmental burdens compared with conventional approaches, although actual benefits depend strongly on the feedstock, processing conditions, purification requirements, and scale.

A 2025 review specifically examining plant-mediated transition-metal oxide nanoparticles reports applications involving NiO, RuO₂, ZnO, CuO, MnO₂, and TiO₂ for supercapacitors. It also identifies scalability, nanoparticle stability, and reaction-condition optimization as persistent challenges.

Structural and Morphological Characterization

Comprehensive characterization is essential because electrochemical performance cannot be interpreted reliably without establishing material composition and structure.

X-Ray Diffraction

X-ray diffraction (XRD) is commonly employed to identify crystalline phases, lattice parameters, crystallinity, and possible secondary phases. The average crystallite size can be estimated using the Scherrer equation:

$$D = \frac{K\lambda}{\beta \cos \theta}$$

where D represents crystallite size, K is the shape factor, λ is the X-ray wavelength, β is the corrected full width at half maximum, and θ is the diffraction angle.

It should be emphasized that crystallite size obtained through the Scherrer equation is not necessarily equivalent to particle size observed by electron microscopy.

Scanning Electron Microscopy

Scanning electron microscopy (SEM) provides information about surface morphology, particle aggregation, pore structures, and electrode architecture. For energy-storage applications, SEM can reveal whether a synthesis route produces dense particles or open hierarchical structures. Porous and interconnected structures generally provide improved electrolyte accessibility compared with highly aggregated particles.

Transmission Electron Microscopy

Transmission electron microscopy (TEM) offers higher-resolution information regarding particle size, morphology, lattice fringes, interfaces, and defects. High-resolution TEM can identify crystallographic planes, while selected-area electron diffraction can provide complementary structural information.

Energy-Dispersive X-Ray Spectroscopy

Energy-dispersive X-ray spectroscopy (EDS/EDX) is typically coupled with SEM or TEM to determine elemental composition and distribution. Elemental mapping is particularly important for binary and ternary transition-metal

compounds because uniform elemental distribution can be critical to reproducible electrochemical performance.

Fourier-Transform Infrared Spectroscopy

FTIR spectroscopy identifies characteristic chemical bonds and functional groups. Although it does not provide complete crystallographic information, it is valuable for detecting metal-oxygen, metal-sulfur, hydroxyl, carbonate, and organic residues.

Raman Spectroscopy

Raman spectroscopy provides information about vibrational modes, structural disorder, phase composition, and defects. It can be especially useful for carbon-containing transition-metal composites.

Surface-Area and Porosity Analysis

Brunauer-Emmett-Teller (BET) analysis provides specific surface area, while Barrett-Joyner-Halenda (BJH) analysis can provide pore-size information.

High surface area alone, however, should not be interpreted as proof of superior electrochemical performance. Pores must also be accessible to electrolyte ions, and excessive microporosity may limit ion transport under high-rate conditions.

Electrochemical Characterization

Cyclic Voltammetry

Cyclic voltammetry (CV) is widely used to determine electrochemical behavior. For an ideal electric double-layer capacitor, CV curves are approximately rectangular. Redox-active transition-metal materials typically produce distinct oxidation and reduction features. The scan rate dependence provides information about reaction kinetics and charge-storage mechanisms. A strong change in peak position with increasing scan rate can indicate kinetic limitations and polarization.

Galvanostatic Charge-Discharge

Galvanostatic charge-discharge (GCD) measurements provide specific capacity or specific capacitance, rate capability, and cycling stability. For a supercapacitor electrode, specific capacitance may be estimated using:

$$C_s = \frac{I \Delta t}{m \Delta V}$$

where I is the discharge current, Δt is discharge time, m is active material mass, and ΔV is the potential window.

Energy density can be expressed as:

$$E = \frac{1}{2} C V^2$$

while power density can be approximated as:

$$P = \frac{E}{\Delta t}$$

These equations demonstrate why increasing operating voltage can have a particularly strong effect on energy density.

Electrochemical Impedance Spectroscopy

Electrochemical impedance spectroscopy (EIS) is valuable for determining charge-transfer resistance, electrolyte resistance, diffusion behavior, and interfacial processes. A Nyquist plot commonly contains a high-frequency intercept representing solution resistance and a semicircle associated with interfacial charge-transfer processes. Lower charge-transfer resistance generally indicates more favorable electron-transfer kinetics, although interpretation should consider the complete equivalent circuit and electrode configuration.

Cycling Stability

Cycling stability is critical for practical applications. A material showing extremely high initial capacitance or capacity but rapid degradation may have limited practical value.

Transition-metal materials can undergo:

- phase transformation;
- dissolution;
- particle pulverization;
- volume expansion;
- surface reconstruction;
- loss of electrical contact; and
- electrolyte-induced degradation.

Recent reviews identify structural stability as one of the principal barriers to the practical application of transition-metal oxide electrodes.

Structure-Property Relationships

The performance of transition-metal nanomaterials is strongly dependent on structure.

Particle Size

Reducing particle size can shorten ion-diffusion distances and increase surface-to-volume ratio. However, extremely small particles can exhibit

increased surface reactivity and aggregation. Therefore, an optimal particle size rather than simply the smallest possible particle size is desirable.

Porosity

Hierarchical porosity can provide complementary functions. Micropores can contribute to charge storage, mesopores can facilitate ion transport, and macropores can provide electrolyte reservoirs. Transition-metal-based porous architectures have received substantial attention because their interconnected structures can simultaneously increase active surface area and improve electrolyte accessibility.

Defect Engineering

Vacancies and lattice defects can alter electronic structure, increase active sites, and modify adsorption or ion-transport behavior. For sulfides, sulfur vacancies are increasingly explored as a method for adjusting electronic properties and exposing additional active sites. However, excessive defects may reduce structural stability. Consequently, defect concentration must be optimized rather than maximized.

Mixed-Metal Systems

Combining two or more transition metals can produce synergistic effects.

For example, binary and ternary compounds may provide:

- multiple redox couples;
- modified electronic structures;
- improved electrical conductivity;
- greater structural diversity; and
- enhanced electrochemical activity.

Recent reviews of binary and ternary transition-metal composites emphasize their potential for improving supercapacitor performance through complementary redox behavior and improved structural architectures.

Transition-Metal Nanomaterials in Supercapacitors

Supercapacitors are generally classified according to their charge-storage mechanisms as electric double-layer capacitors, pseudocapacitors, and hybrid devices. Transition-metal compounds are particularly important in pseudocapacitive and

hybrid systems because they undergo reversible Faradaic reactions.

The major advantage of transition-metal electrodes is their ability to provide higher charge storage than purely carbon-based electric double-layer electrodes. Their disadvantages include lower intrinsic conductivity for many oxides and possible structural degradation.

Hybrid supercapacitors attempt to combine battery-type and capacitive behavior. Recent work distinguishes battery-type electrodes from pseudocapacitive materials and emphasizes that the underlying electrochemical mechanisms should not be treated as interchangeable.

Transition-metal oxides are particularly important in these systems. Recent literature highlights the use of NiO, Co₃O₄, MnO₂, vanadium oxides, and mixed-metal oxides.

Transition-metal sulfides provide another route toward higher performance. Their favorable electronic conductivity and redox chemistry have stimulated extensive research into binary and ternary sulfide architectures.

Applications in Batteries

Transition-metal nanomaterials are also important in rechargeable batteries.

Lithium-Ion Batteries

Transition-metal oxides can function as anodes or cathodes depending on their chemistry.

Nanostructuring can improve reaction kinetics and accommodate mechanical changes. However, conversion-type oxides can experience substantial volume variation during lithiation and delithiation. Recent research on binary transition-metal oxides has focused on controlling micro/nanostructure and understanding conversion mechanisms to improve lithium-storage performance.

Sodium-Ion Batteries

Sodium-ion batteries are receiving increased attention because sodium is abundant and potentially less expensive than lithium. Layered transition-metal oxides are among the important cathode families being investigated. However, the larger sodium ion creates challenges related to diffusion kinetics and structural stability.

Consequently, morphology control, composition engineering, and defect management are important strategies.

Lithium-Ion Capacitors

Lithium-ion capacitors combine battery-type and capacitor-type electrodes. Transition-metal oxides are attractive because they can provide high lithium-storage capacity while retaining relatively favorable kinetics. A recent review identifies transition-metal oxides as promising lithium-ion capacitor anodes because of their lithium-storage capability, abundance, tunable structure, and potentially favorable cost.

Composite and Hybrid Architectures

One of the most effective approaches for improving transition-metal nanomaterials is integration with conductive materials.

Carbon Nanotubes

Carbon nanotubes provide conductive pathways and mechanical support. They can reduce particle aggregation and improve electrical contact.

Graphene

Graphene possesses high electrical conductivity and a two-dimensional structure. Transition-metal oxide/graphene and sulfide/graphene composites can combine Faradaic activity with conductive networks.

MXenes

MXenes provide high conductivity and hydrophilic surfaces. Their layered structures make them promising substrates for anchoring transition-metal nanomaterials.

Conducting Polymers

Polyaniline, polypyrrole, and related polymers can improve flexibility and conductivity. However, repeated swelling and contraction of conducting polymers may cause long-term degradation.

Recent reviews identify carbon materials, conductive polymers, MXenes, and metal-organic frameworks as important partners for improving the conductivity and structural stability of transition-metal sulfides.

Green and Sustainable Synthesis

Although nanomaterials can improve energy-storage performance, their synthesis should not

create disproportionate environmental costs. Conventional synthesis can require high temperatures, organic solvents, toxic reducing agents, or complex purification procedures. Green synthesis attempts to minimize these impacts through safer solvents, biological reducing agents, renewable feedstocks, and lower-energy processing.

Plant extracts contain compounds such as polyphenols, flavonoids, sugars, proteins, and organic acids that can participate in metal-ion reduction and stabilization.

The principal advantages include:

- reduced reliance on hazardous chemicals;
- use of renewable biological resources;
- potentially lower processing temperatures;
- reduced environmental impact; and
- opportunities for waste valorization.

Nevertheless, green synthesis should not automatically be considered sustainable. Reproducibility of plant extracts, seasonal variation, purification requirements, nanoparticle toxicity, and large-scale processing must be systematically assessed. Recent research specifically identifies scalability and reaction-condition control as unresolved problems for plant-mediated transition-metal oxide synthesis.

Current Challenges

Despite substantial progress, several barriers prevent widespread commercialization.

Poor Intrinsic Conductivity

Many transition-metal oxides exhibit inadequate electrical conductivity. This limitation can be addressed through carbon integration, doping, defect engineering, and nanoscale architecture.

Structural Degradation

Repeated insertion/extraction of ions or Faradaic reactions can produce mechanical stress and phase changes.

Hydrous transition-metal oxides are particularly interesting because structural water can influence ion transport and electrochemical reaction pathways. Recent research combining first-principles calculations with operando characterization has provided greater insight into these mechanisms.

Particle Aggregation

Nanoparticles possess high surface energy and naturally tend to aggregate. Aggregation decreases accessible surface area and limits electrolyte penetration.

Reproducibility

Small changes in pH, temperature, precursor concentration, reaction time, or calcination conditions can substantially alter nanostructure. Standardized synthesis protocols are therefore necessary for meaningful comparison between studies.

Scale-Up

A material that performs well in a laboratory coin cell may not retain the same characteristics during kilogram- or ton-scale manufacturing.

Scale-up introduces challenges in:

- heat and mass transfer;
- mixing;
- precursor uniformity;
- particle-size control;
- drying;
- calcination;
- electrode fabrication; and
- quality control.

Laboratory-to-Device Gap

Many publications report high specific capacitance or capacity using very small active-material masses. However, practical devices require sufficient areal loading, realistic electrode thickness, appropriate electrolyte quantities, and balanced electrode masses.

Consequently, device-level metrics should complement material-level measurements.

Future Research Directions

Future research should move from isolated material optimization toward integrated structure-mechanism-device studies.

First, **rational defect engineering** should be developed to control vacancies without compromising structural stability.

Second, **multimetal systems** can be explored to combine multiple redox couples and tune electronic structures.

Third, **hierarchical architectures** should be designed to balance surface area, pore accessibility, mechanical stability, and volumetric energy density.

Fourth, **green synthesis** should be coupled with life-cycle assessment rather than evaluated solely on the basis of biological reagents.

Fifth, operando characterization should become more widely adopted. Ex situ characterization provides valuable structural information but may fail to capture transient phase transformations occurring during charging and discharging. Operando XRD, Raman spectroscopy, X-ray absorption spectroscopy, and advanced microscopy can reveal how electrode structures evolve under realistic operating conditions.

Sixth, computational approaches such as density functional theory and molecular dynamics can complement experimental research by predicting defect formation, ion adsorption, diffusion pathways, and electronic structures.

Finally, researchers should report practical metrics including areal capacity, volumetric capacity, active-material loading, full-cell energy density, cycling under realistic current densities, and performance at relevant temperatures.

Recent reviews of emerging energy-storage nanomaterials similarly emphasize that future progress requires stronger relationships between nanoscale architecture, electrochemical mechanisms, durability, and practical device requirements.

Proposed Research Framework

The synthesis and evaluation of transition-metal nanomaterials can be organized into the following research framework:

Figure 1: Workflow for Energy Storage Nanomaterials R&D




Figure 1: Workflow for Energy Storage Nanomaterials R&D

This framework emphasizes that synthesis and characterization should not be treated as independent stages. Instead, characterization results should directly guide subsequent optimization of synthesis conditions.

Conclusion

Transition-metal nanomaterials represent an important class of advanced electrode materials for next-generation energy-storage technologies. Their variable oxidation states, diverse crystal structures, tunable morphology, and rich electrochemical chemistry make them suitable for supercapacitors, lithium-ion batteries, sodium-ion batteries, lithium-ion capacitors, and related hybrid systems.

The literature demonstrates that nanoscale engineering can improve electrochemical behavior by increasing active surface area, shortening diffusion pathways, enhancing electrolyte accessibility, and generating favorable defect structures. Transition-metal oxides remain particularly important because of their chemical diversity and strong redox activity, while transition-metal sulfides, nitrides, hydroxides,

and mixed-metal compounds offer additional opportunities for improving conductivity and charge-storage kinetics. Recent 2024–2025 reviews confirm continued progress in porous architectures, mixed-metal composites, sulfide electrodes, nitride structures, and green synthesis. Nevertheless, high laboratory performance alone is insufficient to establish practical suitability. Poor conductivity, particle aggregation, structural degradation, volume changes, limited reproducibility, environmental concerns, and difficulties in scaling synthesis remain major challenges. The development of conductive composites, hierarchical structures, defect-controlled materials, and environmentally responsible synthesis routes can help address these limitations.

Future research should therefore prioritize mechanism-driven materials design, operando characterization, scalable synthesis, realistic device testing, and sustainability assessment. In particular, transition-metal nanomaterials should be evaluated under practical electrode loadings and full-cell configurations rather than solely

through idealized half-cell or three-electrode measurements. Such an integrated approach can accelerate the transition from laboratory-scale nanomaterial discovery to reliable, durable, and commercially relevant energy-storage technologies.

REFERENCES

- Alharbi, A. (2025). Boosting supercapacitor performance through innovative transition metal-based electrode materials. *RSC Advances*, 15, 34551–34582. <https://doi.org/10.1039/D5RA02905H>
- Althomali, R. H., & Adeosun, W. A. (2023). Wet chemically synthesized metal oxides nanoparticles, characterization and application in electrochemical energy storage: An updated review. *Synthetic Metals*, 298, 117424. <https://doi.org/10.1016/j.synthmet.2023.117424>
- Arul Saravanan, R. S., Bejigo, K. S., & Kim, S.-J. (2023). Scope and significance of transition metal oxide nanomaterials for next-generation Li-ion batteries. *Materials Chemistry Frontiers*. <https://doi.org/10.1039/D3QM00226H>
- Deka, S. (2023). Nanostructured mixed transition metal oxide spinels for supercapacitor applications. *Dalton Transactions*, 52, 839–856. <https://doi.org/10.1039/D2DT02733J>
- Mitchell, J. B., Chagnot, M., & Augustyn, V. (2023). Hydrous transition metal oxides for electrochemical energy and environmental applications. *Annual Review of Materials Research*, 53, 1–23. <https://doi.org/10.1146/annurev-matsci-080819-124955>
- Oyelade, O. V., Idris, A., Mohammed, M., Gimba, S., Felix, J., Okike, O., Obagboye, L., Aisida, S. O., & Ezema, F. I. (2025). Green synthesis of some selected transition metal oxide nanoparticles for energy storage applications in supercapacitors. *Journal of the Indian Chemical Society*, 102, 101666. <https://doi.org/10.1016/j.jics.2025.101666>
- Ran, F., Hu, M., Deng, S., Wang, K., Sun, W., Peng, H., & Liu, J. (2024). Designing transition metal-based porous architectures for supercapacitor electrodes: A review. *RSC Advances*, 14, 11482–11512. <https://doi.org/10.1039/D4RA01320D>
- Xu, et al. (2024). Mechanism research progress on transition metal compound electrode materials for supercapacitors. *Rare Metals*. <https://doi.org/10.1007/s12598-024-02808-4>
- Zhao, C., Yao, S., Li, C., An, Y., Zhao, S., Sun, X., Wang, K., Zhang, X., & Ma, Y. (2024). Recent advances in transition metal oxides as anode materials for high-performance lithium-ion capacitors. *Chemical Engineering Journal*. <https://doi.org/10.1016/j.cej.2024.154535>
- Zhu, M., Wang, D., Ge, Z., Pan, L., Chen, Y., Wang, W., Mitsuzaki, N., Jia, S., & Chen, Z. (2025). Recent advances in transition metal sulfide-based electrode materials for supercapacitors. *Chemical Communications*, 61, 8314–8326. <https://doi.org/10.1039/D5CC01411E>
- Zia, J., & Tejaswini, M. S. S. R. (2025). Advancements in binary and ternary transition metal-based composites for high-performance supercapacitors: A comprehensive review. *RSC Advances*, 15, 9055–9080. <https://doi.org/10.1039/D5RA00528K>

Zhou, et al. (2024). Developments and key challenges in micro/nanostructured binary transition metal oxides for lithium-ion battery anodes. *Journal of Energy Storage*, 84, 110850.

<https://doi.org/10.1016/j.est.2024.110850>

0

